

camattini spa thermosetting resins

 Resin
PL 314

 Hardener
G 114

 Mixing ratio by weight
100:17

Applications: Encapsulation of: transformers of small and medium size, capacitors, voltage regulators, components particularly sensitive to thermo-mechanical stress.

Processing. Manual casting. Undervacuum casting. Room temperature curing. It is advisable to dry or pre-heat the components to be casted.

Description: Two components polyurethane system filled with no-abrasive fillers. Self-extinguishing. The system is free from solvents and halogens. Flexible. Good electrical properties. Good thermal resistance. The system is UL 94 V-0 listed (File E116643).

SYSTEM SPECIFICATIONS

Resin

Viscosity at:	25°C	IO-10-50	mPas	4.500	7.500
Density at:	25°C	IO-10-51 (ASTM D 1475)	g/ml	1,39	1,43
Gelation time	50°C	IO-10-52b (UNI 8701)	min	27	35

Hardener

Viscosity at:	25°C	IO-10-50	mPas	120	180
NCO groups		IO-10-55	% peso	24,80	26,50

TYPICAL SYSTEM CHARACTERISTICS

Processing Data

Mixing ratio by weight	each 100 g resin	g	100:17
Mixing ratio by volume	each 100 ml resin	ml	100:20
Resin Colour			Various colours
Hardener Colour			Brown Blue

Density at:	25°C Hardener	IO-10-51 (ASTM D 1475)	g/ml	1,18	1,21
Pot life at:	25°C (3.000 mPas)	IO-10-50 (*)	min	10	15

Initial mixture viscosity at:	25°C	IO-10-50	mPas	1.000	2.000
Gelation time	25°C (15ml;6mm)	IO-10-73 (*)	h	1	2
Gelation time	25°C 100ml	IO-10-52a (UNI 8701)	min	110	130
Demoulding time	25°C (15ml;6mm)	(*)	h	6	8
Post-curing	60°C	(**)	h	(8 - 10)	

TYPICAL CURED SYSTEM PROPERTIES
Properties determined on specimens cured: 24 h TA + 15 h 60°C

Surface				Bright
Density 25°C	IO-10-54 (ASTM D 792)	g/ml	1,37	1,41
Hardness	IO-10-68 (ASTM D 2240)	Shore A/15	74	80
Glass transition (Tg)	IO-10-69 (ASTM D 3418)	°C	- 17	-23
Water absorption (24h RT)	IO-10-70 (ASTM D 570)	%	0,2	0,3
Water absorption (2h 100°C)	IO-10-70 (ASTM D 570)	%	1,0	1,2
Linear thermal expansion (Tg +10°C)	IO-10-71 (ASTM E 831)	10 ⁻⁶ /°C	160	180
Thermal shock (n°10 cycles passed)	IO-10-67 (inserto metallico Olyphant)	°C	- 55	+ 180
Flammability	IO-10-68 (UL 94 V-0)	mm	6,4	
Max recommended operating temperature	IEC 60085 (***)	°C	130	
Thermal conductivity	IO-10-87 (ASTM C518)	W/(m°K)	0,47	0,54
Dielectric constant at: 25°C	IO-10-59 (ASTM D 150)		7,5	8,5
Loss factor at: 25°C	IO-10-59 (ASTM D 150)	x 10 ⁻³	75	90
Volume resistivity at: 25°C	IO-10-60 (ASTM D 257)	Ohm x cm	1 x 10 ¹¹	5 x 10 ¹¹
Dielectric strength	IO-10-61 (ASTM D 149)	KV/mm	18	21
Tracking index	IEC 60112	CTI	> 600	
Flexural strength	IO-10-66 (ASTM D 790)	MN/m ²		na
Strain at break	IO-10-66 (ASTM D 790)	%		na
Flexural elastic modulus	IO-10-66 (ASTM D 790)	MN/m ²		na
Tensile strength	IO-10-63 (ASTM D 638)	MN/m ²	1,5	2,5
Elongation at break	IO-10-63 (ASTM D 638)	%	25	35

IO-00-00 = Camattini's test method. The correspondent international method is indicated whenever possible.

nd = not determined na = not applicable RT = laboratory room temperature (23±2°C)

 Conversion units: 1 mPas = 1 cPs 1MN/m² = 10 kg/cm² = 1 MPa

(*) for larger quantities pot life is shorter and exothermic peak increases

(**) the brackets mean optionality

(***) the maximum recommended operating temperature is given on the basis of available laboratory information. Users should make their own assessments to verify the real component thermal class which is the result of the applied construction technology and used protective materials.

Instructions: In pre-filled products it is a good practice to check and carefully rehomogenize the material if some settlement is present. Add the proper quantity of the hardener to the resin, mix carefully. Avoid air trapping. For some applications it can be useful pre-heat the components and/or carry on a deaeration step under vacuum of the mixture before casting.

Post-curing For room temperature curing system the post-curing allows the fast stabilization of the material and the obtainment of the best electrical and mechanical properties. During curing process it is advisable to avoid thermal variations higher than 10°C/hour.

Storage: Polyurethane resins and the isocyanate based hardeners can be stored for six months in the original sealed containers kept in a cool and dry place. The hardeners may present an increase in viscosity that do not change the cured system properties. After that period, or if the material has been stocked in anomalous conditions, pre-filled resins can be settled down and their use is possible only if they are accurately re-homogenized with the help, if necessary, of a mechanical mixer. Both components are moisture sensitive therefore it is a good practice to close the vessels immediately after each use. Moisture absorption may cause the expansion of the product during application and/or the hardener may crystallize during storage.

Handling precautions: Refer to the data sheet and comply with regulations relating to industrial health and waste disposal.

emission date:	September	1998/R&S
revision n° 02	March	2004/R&S

The information given in this publication is based on the present state of our technical knowledge but buyers and users should make their own assessments of our products under their own application conditions.